

Water-based Impregnation for Wood Substrates

	Weight (%)		
NeoCryl® XK 98	89.0	Acrylic Binder	DSM Corporation
Ethyl Di Glycol	3.0	Co-solvent	-
Water	3.0	Solvent	-
TEGO® Phobe 6600	5.0	Hydrophobing Agent	Evonik
Total	100.0		