

# Water-based Primer for Substrates with Normal Penetration

	Weight (%)		
MOWILITH® DM 760	12.0	Hydrosol	Celanese Corporation
ACTICIDE® MBS	0.2	Biocide	THOR
Water	77.8	Solvent	-
TEGO® Phobe 6510	10.0	Hydrophobing Agent	Evonik
Total	100.0		